

The following is a complete listing of all claims in the application, with an indication of the status of each:

**Listing of claims:**

- 1           1. (currently amended) A polarizing filter having a laminate structure,  
2           comprising:
  - 3               a first group of dielectric thin film materials;
  - 4               a second group of dielectric thin film materials; and
  - 5               a third layer of dielectric thin film material,
  - 6               wherein a plurality of dielectric materials different from one another in  
7               refractive index with respect to a wavelength of incident light are classified  
8               into said first group and said second group so that a maximum value among  
9               the refractive indices of the dielectric materials belonging to said first group is  
10              lower than a minimum value among the refractive indices of the dielectric  
11              materials belonging to said second group;
  - 12              wherein at least one layer of dielectric thin film selected from the  
13              dielectric materials belonging to said first group and at least one layer of  
14              dielectric thin film selected from the dielectric materials belonging to said  
15              second group are alternately laminated to form said laminate structure, said  
16              laminate structure being mounted on a transparent flat substrate beginning  
17              with a first layer adjacent to said transparent flat substrate;
  - 18              wherein said third layer of dielectric thin film has a refractive index  
19              which is higher than the maximum value selected from said refractive indices  
20              of the dielectric materials belonging to said first group and which is lower  
21              than the minimum value selected from said refractive indices of the dielectric  
22              materials belonging to said second group and is laminated on an outermost

23 surface of said laminate structure, said laminate structure being between said  
24 third layer and said transparent flat substrate; ~~and~~  
25 wherein said first layer includes the dielectric thin film selected from  
26 the dielectric materials belonging to said second group; and  
27 wherein said polarizing filter polarizes non-polarized light into  
28 polarized light having an s-polarized light component and a p-polarized light  
29 component, the transmittance ratio of the s-polarized light component to the p-  
30 polarized light component being in the range of 0.2 to 1.0.

1 2. (canceled)

1 3. (previously presented) A polarizing filter according to Claim 1, wherein  
2 one to four layers of dielectric thin films selected from said first group and one  
3 to four layers of dielectric thin films selected from said second group are  
4 laminated alternately on said transparent flat substrate.

1 4. (previously presented) A polarizing filter according to Claim 1, wherein a  
2 refractive index difference with respect to the wavelength of incident light  
3 between adjacent dielectric thin films selected from the dielectric materials  
4 belonging to said first and second groups respectively is in a range of from  
5 0.15 to 1.2, both inclusively.

1 5. (previously presented) A polarizing filter according to Claim 1, wherein  
2 optical film thickness of each of said dielectric thin films is in a range of  
3  $0.25\lambda \pm 0.15\lambda$  in which  $\lambda$  is a wavelength of incident light.

1        6. (previously presented) An optical device using a polarizing filter defined  
2        in Claim 1, wherein an angle of incidence on said polarizing filter is in a range  
3        of from 20 to 70 degrees.

1        7-8. (canceled)

1        9. (previously presented) A polarizing filter according to claim 1, wherein a  
2        total number of layers of dielectric thin film is at least three layers and not  
3        larger than seven layers.

1        10. (currently amended) A polarizing filter according to claim 1, wherein the  
2        refractive index of said layer on an outermost surface is 1.62 ~~or 1.46~~.

1        11. (previously presented) A polarizing filter according to claim 1, wherein  
2        said layers are constructed by three layers, the refractive index of the first layer  
3        is 2.13, the refractive index of the second layer is 1.46, and the refractive  
4        index of the layer on an outermost surface is 1.62.

1        12. (currently amended) A polarizing filter according to claim 1, wherein  
2        said layers are constructed by three layers, the refractive index of the first layer  
3        is 2.13, the refractive index of the second layer is 1.40, and the ~~first~~ refractive  
4        index of ~~the said layer on an~~ outermost ~~layer~~ surface is 1.46.

1        13. (currently amended) A polarizing filter according to claim 1, wherein  
2        said at least three layers are constructed by seven layers, the refractive indexes  
3        of the first to sixth layers are 2.13, 1.46, 2.13, 1.46, 2.13 and 1.46,

N36-136495 M/TH

**AMENDMENT WITH RCE**

02410250aa

Amendment dated 02/07/2005

Reply to office action mailed 11/05/2004

4        respectively, and the refractive index of ~~the said layer on an~~ outermost ~~layer~~  
5        surface is 1.62.

1        14. (currently amended) A polarizing filter according to claim 1, wherein  
2        said at least three layers are constructed by five layers, the refractive indexes  
3        of the first to fourth layers are 2.13, 1.46, 2.13 and 1.46, respectively, and the  
4        ~~first~~ refractive index of ~~the said layer on an~~ outermost ~~layer~~ surface is 1.62.

1        15-22. (canceled)